



ECP Crack Injection Resins

ECP Epoxy is a 100% solids, two-component, multi-viscosity, moisture insensitive epoxy designed for deep penetration to restore the structural integrity of the foundation. Unique wetting properties allow maximum penetration of epoxy into cracks as small as .005”.

ECP Polyurethane Resins are a innovative blend of hydrophobic/hydrophlic polyurethane resins designed to provide the ultimate solution for crack repair and void grouting applications. In contact with water, ECP Polyurethane Resins will expand up to 20 times its original volume creating a permanent, flexible and water-tight seal.

Technical Data

ECP PFLV

Performance Properties
Test/Test Method Results

Water Absorption ASTM D-2127	<1%
Shrinkage ASTM D-2126	<0%
Color	Amber Clear
Viscosity	400 cps
Density ASTM D-1622	60lbs/ft
Tear Strength ASTM D-624	400 psi
Tensile Strength ASTM D-638	2000 psi
Elongation ASTM D-638	100%

ECP Epoxy

Performance Properties
Test/Test Method Results

Thin Film Set-Time @ 77°	3-5 hr
Full Cure Time	24 hr
Comp. Strength	14480 psi
Tensile Strength	8315 psi
Tensile Elong. ASTM D-638	8.9%
Coefficient of Shrinkage	<.001
Heat Deflection Temp.	>120°
Shore D Hardness	80-75
Water Absorption	.1989%
Mixed Viscosity	LV 150 cps MV 650 cps HV 13000 cps
Color Mixed	Amber
Mix Ratio	2:1

Packaging: Epoxy 16.5 oz dual cartridge,
Polyurethane 22 oz dual cartridge.
Both available by gallon on request.

ECP PF1C

Performance Properties
Test/Test Method Results

Water Absorption ASTM D-2127	<1%
Shrinkage ASTM D-2126	<0%
Color	Clear
Viscosity	600 cps
Density ASTM D-1622	65lbs/ft
Tear Strength ASTM D-624	400 psi
Tensile Strength ASTM D-638	2200 psi
Elongation ASTM D-638	400%

ECP HYFO

Performance Properties
Test/Test Method Results

Viscosity	230 cps
Shear ASTM D-273	175 psi
Tensile ASTM D-1623	375 psi
Elongation ASTM D-1623	410%
Color	Milky

**EARTH
CONTACT
PRODUCTS**

1-866-327-0007

15612 S Keeler Terr.
Olathe, Ks 66062
Phone:913-393-0007
Fax:913-393-0008
info@getecp.com
www.getecp.com

ECP